

Certificate of Analysis

Test Day : 2015. 04. 14.

Product : Slim Film 50

Spec : 50 μm \times mm \times R/L

ITEM	UNIT	Standard	Result	Test Method	
Haze	%	85 \pm 10	84	ASTM D 1003	
Thickness	μm	50 \pm 15	61	Thickness Gauge (1/1000)	
Basis Weight	g/m ²	45 \pm 3	45	MW-II	
Tensile strength at Break	MD	N/cm ²	1500 \pm 200	1473	ASTM D 882
	CD			1673	
Elongation at Break	MD	%	12 \pm 1.2	13	ASTM D 882
	CD			10 \pm 1.0	
Tear strength at Break	MD	N/cm ²	1300 \pm 200	1423	ASTM D 1004
	CD			1248	

신 흥 화 학 주 식 회 사
 신 흥 화 학 주 식 회 사